

QUALITY ASSURANCE SYSTEM – PRODUCT DATA SHEET

<u>Product reference N°</u>	AS11 (Suffix with R when Red ^a) Issue N° 10
<u>Product Description</u>	HRA 0/2 surf 40/60 or 100/150 ^C rec Proprietary Mix
<u>Trade Description</u>	Sand Carpet
<u>Aggregate</u>	Blend of Basalt Dust and Pit Sand ^b

Specification Details

John Wainwright proprietary specification:

<u>Sieve Size</u>	<u>Conformance Specification</u>	<u>Declared Target</u>
6,3	100 – 100	100
2	85 – 98	93
0,500	53 – 73	63
0,250	24 – 44	34
0,063	10 – 14	12
Target Binder Content %	9,2 – 10,4	9,8
Minimum Layer Thickness	Machine 20mm	
Binder Penetration	Machine: 40/60 or 100/150 Handlay: Generally 100/150	
Target mixing Temperature	100/150	140-170°C
Target Mixing Temperature	40/60	160-190°C

^CDenotes Binder Penetration as specified

Recommendations of use

^aAvailable in RED on request.

Regulating, Bridge Decks, Shaping, Ramps etc.

For further technical information regarding application, specification and use, consult the **Quarry Laboratory**.

The finish of the surface can be blemished if equipment such as rollers are not cleaned before use.

^bSupplied by the current approved sand source.

Issued by:

Ian Timberlake



Date Issued: 03/01/08