

QUALITY ASSURANCE SYSTEM – PRODUCT DATA SHEET

<u>Product reference N°</u>	AS15	Issue N° 13
<u>Product Description</u>	HRA 30/14F surf 40/60 des PSV60 or 65 ^a	
<u>Trade Description</u>	30% 14mm HRA	
<u>Course Aggregate</u>	^a Gritstone PSV ₆₀ or PSV ₆₅	
<u>Aggregate Fine</u>	Pit Sand ^b	

Specification Details

EN13108-4 Table 4

<u>Sieve Size</u>	<u>Conformance Specification</u>	<u>Declared Target</u>
20	98 – 100	100
14	90 – 100	98
10	67 – 81	74
6.3	NPD	71
2	60 – 70	65
0.5	48 – 56	52
0.25	31 – 39	35
0.063	7 – 11	9
Target Binder Content %	6.3 – 7.5	6.9

Minimum Layer Thickness	Machine 35mm	
Binder Penetration	Machine:	40/60
Target Mixing Temperature	40/60	160-190°C

Additional Requirements:

Stability: 6.5kN (40/60) in accordance with BS 594987: 2010 Annex H

^bSupplied by the current approved sand source.

Recommendations of use

Heavily trafficked or high speed roads, lorry parks and any area, where the use of Asphalt with a high PSV coarse aggregate is required.

We would generally recommend that customers do not attempt to use **40/60** material when the ambient temperature is below 3°C or the substrate temperature is below freezing.

Issued by:

Ian Timberlake



Date Issued: 2/4/13