

**QUALITY ASSURANCE SYSTEM – PRODUCT DATA SHEET**

**Product reference N°** CS11 Issue N° 4

**Product Description** Basalt Scalpings

**Trade Description** As Above

**Specification Details**

Not manufactured or supplied to British Standard Requirements.

<u>BS Sieve Size</u>	<u>6F4 - Grading Limits %</u>	<u>Typical Result %</u>
63mm	100	-
37.5mm		100
31.5mm	75 to 99	98
20mm		81
16mm	50 to 90	69
14mm		69
10mm		52
8mm	30 to 75	44
4mm	15 to 60	28
1mm	0 to 30	15
63µm	0 to 15	6.0

**Comments**

Moisture Contents: Range = **1 to 6%** Mean = **4.4%**

**Recommendations of use**

Although, Moons Hill Scalpings comply with **Type 2, Granular Sub – base** grading requirements, it is generally found to have a Plasticity Index in excess of the specified maximum value **i.e. 6**. Will also meet **SHW, Series 600** requirements for **Class 6N & 6F4** fill material.

Basalt Scalpings are generally found suitable for a wide range of applications, such as back filling, road foundations, farm tracks, hard standings and any other customer specified application. Basalt scalpings also have the advantage over Limestone scalpings as they tend not to be water sensitive **i.e.** do not breakdown when wet under trafficking.

Issued by:

Ian Timberlake



Date Issued: 18/9/06