

QUALITY ASSURANCE SYSTEM – PRODUCT DATA SHEET

Product reference N° D20 Issue N° 2

Product Description AC 20 bin 160/220 fluxed PSV55

Trade Description 20mm 28 day deferred binder course

Aggregate All Basalt

Specification Details

EN13108-1

<u>Test Sieve (mm)</u>	<u>Conformance Specification</u>	<u>Declared Target</u>
31,5	98 – 100	100
20	86 – 100	95
10	48 – 66	57
6,3	38 – 56	47
2	13 – 27	20
0,250	0 – 10	5
0,063	0 – 6	3
Declared Binder Content %	3.4 – 4.6	4.0

Nominal Layer Thickness (mm) 50 - 100

Binder Penetration Handlay: 160/220 fluxed

Target Mixing Temperature 70 to 90°C

Recommendations of use

For reinstatements, patch repairs, ramping off, potholes etc.

NOTE: As this material contains bitumen modified by the addition of light oil it may not obtain full strength immediately upon application.

For further technical information regarding application, specification and use, consult the **Quarry Laboratory**.

Issued by:

Ian Timberlake



Date Issued:

21/3/13