

**QUALITY ASSURANCE SYSTEM – PRODUCT DATA SHEET**

**Product reference N°**                      **D6**                      **Issue N° 2**

**Product Description**                      **AC 6 surf 160/220 fluxed PSV55**

**Trade Description**                      **6mm 28 day deferred**

**Aggregate**                      **All Basalt**

**Specification Details**

**EN13108-1**

<u>Test Sieve (mm)</u>	<u>Conformance Specification</u>	<u>Declared Target</u>
10	98 – 100	100
6,3	87 – 100	95
2	19 – 31	25
1	11 – 19	15
0,250	4 – 12	8
0,063	1 – 5	3
Declared Binder Content %	5.5 – 6.5	6.0

Minimum Layer Thickness (mm)                      20 – 25

Binder Penetration                      Handlay:                      160/220 fluxed

Target Mixing Temperature                      70 to 90°C

**Recommendations of use**

For reinstatements, patch repairs, ramping off, potholes etc.

NOTE: As this material contains bitumen modified by the addition of light oil it may not obtain full strength immediately upon application.

For further technical information regarding application, specification and use, consult the **Quarry Laboratory**.

**Issued by:**

**Ian Timberlake**



**Date Issued:**

21/3/13