

QUALITY ASSURANCE SYSTEM – PRODUCT DATA SHEET

Product reference N° D6R Issue N° 1

Product Description AC 6 **Red** surf 160/220 fluxed PSV55

Trade Description 6mm **Red** 28 day deferred

Aggregate All Basalt

Specification Details

EN13108-1

<u>Test Sieve (mm)</u>	<u>Conformance Specification</u>	<u>Declared Target</u>
10	98 – 100	100
6,3	87 – 100	95
2	19 – 31	25
1	11 – 19	15
0,250	4 – 12	8
0,063	1 – 5	3
Declared Binder Content %	5.5 – 6.5	6.0

Minimum Layer Thickness (mm) 20 – 25

Binder Penetration Handlay: 160/220 fluxed

Target Mixing Temperature 70 to 90°C

Recommendations of use

For reinstatements, patch repairs, ramping off, potholes etc.

NOTE: As this material contains bitumen modified by the addition of light oil it may not obtain full strength immediately upon application.

For further technical information regarding application, specification and use, consult the **Quarry Laboratory**.

Issued by:

Ian Timberlake



Date Issued:

23/2/15