

QUALITY ASSURANCE SYSTEM – PRODUCT DATA SHEET

Product reference N° MC1 Issue N° 6

Product Description Coated Grit

Trade Description Bit Grit

Aggregate All Basalt

Specification Details

Wainwright Proprietary Specification:

<u>Test sieve aperture size</u>	<u>Grading Limits %</u>	<u>Target Result %</u>
6,3mm	98 – 100	100
4mm	92 – 100	99
2mm	64 – 76	70
1mm	35 – 43	39
0,25mm	16 – 24	20
0,063mm	5 – 9	7

Target Binder Content % 1,5 – 3,5 3,0

Minimum Compacted Thickness N/A

Binder Penetration Machine: 160/220  
Handlay: 160/220

Target Mixing Temperature 140 – 170°C

Recommendations of use

As delivered it should be suitable for spreading by mechanical gritter

If stored it should remain in this condition for a period of no less than 7 days

Used normally for blinding open Textured Macadam

**Issued by:**

**Ian Timberlake**



**Date Issued:** 03-01-08