QUALITY ASSURANCE SYSTEM – PRODUCT DATA SHEET

Product reference Nº **MC7R** **Issue Nº 7**

Product Description **AC 10 red close surf 70/100, 100/150 or 160/220* PSV55**

Trade Description **As above, or 10mm Red Dense Surface Course**

Aggregate **All Basalt**

Specification Details

EN13108-1

Test Sieve (mm)	Conformance Specification	Declared Target
14	98 – 100	100
10	87 – 100	95
6,3	59 – 73	66
2	25 – 37	31
1	18 – 26	22
0,063	4 – 8	6
Declared Binder Content %	5,0 – 6,0	5,5

Nominal Layer Thickness 30 – 40

Binder Penetration Machine: 70/100, 100/150 or 160/220 as specified
Handlay: Generally 160/220

Target Mixing Temperature 160/200, 100/150 = 140 -170 °C - 70/100 = 150 -180 °C

* As specified

Recommendations of use

Surfacing Roads, Drives, Trench Reinstatements, Vehicle Parking Area's etc. requiring a minimum aggregate Polished Stone value of ***PSV55***.

Can be applied by Machine or by Hand using skilled labour.

The finish of the surface can be blemished if equipment such as rollers are not cleaned before use.

For other applications, contact the **Quarry Laboratory**.

Issued by:
Ian Timberlake

Date Issued: 1/5/14

John Wainwright & Co Ltd Registered Office: Moons Hill Quarry Mendip Road Stoke St Michael Radstock BA3 5JU
Telephone: 01749 840274 Facsimile: 01749 841432 email: info@wainwright.co.uk Website: www.wainwright.co.uk

Sales - Telephone 01749 840111 **Surfacing** - Telephone 01749 841521 Facsimile: 01749 841520