

QUALITY ASSURANCE SYSTEM – PRODUCT DATA SHEET

<u>Product reference N°</u>	PCC2	Issue N° 3
<u>Product Description</u>	PCC 14/20 coated chippings 40/60 PSV70	
<u>Trade Description</u>	Above or 20 Precoats	
<u>Aggregate</u>	14/20 70 PSV Gritstone	

Specification Details

EN13108-4 & PD 6691:2010, Table C.1:

<u>BS Sieve Size</u>	<u>Conformance Specification</u>	<u>Declared Target</u>
31,5	100	100
20	90 – 100	95
14	0 – 25	8
10	0 - 4	3
0,063	0 – 2.0	2
Target Binder Content %	≥1.5	1.5
Binder Penetration	50	-
Maximum Mixing Temperature	160°C	-
Quality of binder coating	<7.5% sand-cover	2

Recommendations of use

Applied to Hot Rolled Asphalt surface courses requiring a minimum aggregate Polished Stone Value of **PSV₇₀** in order to enhance skid resistance in accordance with BS594987:2010.

Normally applied by Machine or Hand using skilled labour.

For other applications, contact the **Quarry Laboratory**.

Issued by:

Ian Timberlake



Date Issued: 3/4/13