

**QUALITY ASSURANCE SYSTEM – PRODUCT DATA SHEET**

**Product reference N°** SMA3R Issue N° 7

**Product Description** Red SMA 6 surf 40/60, 70/100, 100/150 & 160/220<sup>a</sup> PSV55

**Trade Description** Red 6mm SMA

**Aggregate** All Basalt

**Specification Details**

BS EN 13108-5

<u>Sieve Size</u>	<u>Conformance Specification</u>	<u>Declared Target</u>
10	98 – 100	100
6,3	90 – 100	98
4	54 – 68	61
2	29 – 41	35
0,063	9 – 13	11
Target Binder Content %	6.8 – 7.8	7.3
Binder Drainage	0%	
Typical Texture Depth	0,75mm	
Air Voids	3,1%	
Minimum Compacted Thickness	10mm	
<sup>a</sup> Binder Penetration	Machine: Handlay:	40/60, 70/100 or 100/150 100/150 or 160/220
Tack Coat required for thickness less than 20mm:	Bituminous Emulsion (K170)	Applied 0.3 to 0.5 L/m <sup>2</sup>
Target Mixing Temperature	40/60 70/100 100/150 160/220	170 - 200°C 150 - 180°C 140 - 170°C 140 - 170°C

<sup>a</sup>Denotes Binder Penetration as specified.


**Recommendations of use**

To form a durable, deformation resistant, textured, noise and skid reducing Red Surface Course for Roads etc.

Application: Preferable by conventional Asphalt Paver, but can be placed by hand using skilled labour.

The finish of the surface can be blemished if equipment such as rollers are not cleaned before use.

For further technical information regarding application, specification and use, consult the Quarry Laboratory.

Issued by:   
**Ian Timberlake**  
 Date Issued: 25/3/13