

QUALITY ASSURANCE SYSTEM – PRODUCT DATA SHEET

Product reference N° SMA5 Issue N° 3

Product Description SMA 14 surf 40/60, 100/150 PSV68

Trade Description 14mm SMA

Aggregate Gritstone PSV₆₈₊

Specification Details

BS EN 13108-5

<u>Sieve Size</u>	<u>Conformance Specification</u>	<u>Declared Target</u>
20	98 – 100	100
14	87 – 100	95
10	39 – 53	46
6,3	23 – 37	30
2	20 – 32	26
0,063	8 – 12	10.0
Target Binder Content %	6.0 – 7.0	6.5
Binder Drainage	0,0%	
Typical Texture Depth	1,7mm	
Air Voids	2,4%	
Minimum Compacted Thickness	25mm	
Binder Penetration	Machine: 40/60 or 100/150	
Target Mixing Temperature	40/60 170 - 200°C 100/150 140 - 170°C	

Recommendations of use

To form a durable, deformation resistant, textured, noise and skid reducing (PSV₆₈₊) Surface Course for Roads etc.
Application: Preferable by conventional Asphalt Paver, but can be placed by hand using skilled labour.
The finish of the surface can be blemished if equipment such as rollers are not cleaned before use.

For further technical information regarding application, specification and use, consult the **Quarry Laboratory**.

Issued by:

Ian Timberlake



Date Issued:

25/3/13