

QUALITY ASSURANCE SYSTEM – PRODUCT DATA SHEET

<u>Product reference N°</u>	WC8	Issue N° 1
<u>Product Description</u>	0/8 Coarse Basalt Aggregate for Surface Treatment.	
<u>Trade Description</u>	8mm Washed Basalt Chippings	
<u>Specification Details</u>		

Proprietary

<u>BS Sieve Size</u>	<u>Grading Limits %</u>	<u>Typical Result %</u>
14.0mm	100	
10.0mm	100	100
8.0mm	90 - 100	95
6.3mm	60 - 80	70
4.0mm	10 - 20	16
2.0mm	0 - 5	3
1.0mm	0 to 2	1.0
0.63mm	0 - 1	0.0
Fines Content	F_1 Maximum	$f_{0.2}$
Flakiness Index	FI_{20} Maximum	FI_{NR}
Los Angeles coefficient	LA_{30} Maximum	LA_{NR}
Polished Stone Value	PSV_{55} Minimum	PSV_{55}
Aggregate Abrasion Value	AAV_{10} Maximum	AAV_5
Water Absorption	WA_{242} Maximum	$WA_{1.1}$

Recommendations of use

All Surface Dressing applications performed in accordance with **Road Note 39** and requiring a PSV_{55} .
For further technical information regarding application, specification and use, consult the **Quarry Laboratory**.

Issued by:

Ian Timberlake



Date Issued: 12/4/13