

## QUALITY ASSURANCE SYSTEM – PRODUCT DATA SHEET

<b><u>Product reference N°</u></b>	AS11 (Suffix with R when Red <sup>a</sup> ) Issue N° 10
<b><u>Product Description</u></b>	HRA 0/2 surf 40/60 or 100/150 <sup>C</sup> rec Proprietary Mix
<b><u>Trade Description</u></b>	Sand Carpet
<b><u>Aggregate</u></b>	Blend of Basalt Dust and Pit Sand <sup>b</sup>

### **Specification Details**

John Wainwright proprietary specification:

<u>Sieve Size</u>	<u>Conformance Specification</u>	<u>Declared Target</u>
6,3	100 – 100	100
2	85 – 98	93
0,500	53 – 73	63
0,250	24 – 44	34
0,063	10 – 14	12
Target Binder Content %	9,2 – 10,4	9,8
Minimum Layer Thickness	Machine 20mm	
Binder Penetration	Machine: 40/60 or 100/150 Handlay: Generally 100/150	
Target mixing Temperature	100/150	140-170°C
Target Mixing Temperature	40/60	160-190°C

<sup>C</sup>Denotes Binder Penetration as specified

### **Recommendations of use**

<sup>a</sup>Available in RED on request.

Regulating, Bridge Decks, Shaping, Ramps etc.

For further technical information regarding application, specification and use, consult the **Quarry Laboratory**.

The finish of the surface can be blemished if equipment such as rollers are not cleaned before use.

<sup>b</sup>Supplied by the current approved sand source.

**Issued by:**

**Ian Timberlake**



**Date Issued:** 03/01/08