

QUALITY ASSURANCE SYSTEM – PRODUCT DATA SHEET

<u>Product reference N°</u>	AS17	Issue N° 10
<u>Product Description</u>	HRA 15/10F surf 40/60, 70/100 or 100/150 ^{a)} PSV55	
<u>Trade Description</u>	15% 10mm Hot Rolled Asphalt	
<u>Coarse Aggregate</u>	Basalt	
<u>Aggregate Fine</u>	Blend of Basalt Dust and Pit Sand ^{b)}	

Specification Details

EN13108-4 Table 4

<u>Sieve Size</u>	<u>Conformance Specification</u>	<u>Declared Target</u>
14	98 – 100	100
10	92 – 100	100
6.3	78 - 92	85
2	74 - 84	79
0.5	55 - 63	59
0.25	28 - 36	32
0.063	10 - 14	12
Target Binder Content %	7.2 - 8.4	7.8
Minimum Layer Thickness	Machine 30mm	Hand Laid 20mm
Binder Penetration	Machine:	40/60, 70/100 or 100/150
	Handlay:	Generally 100/150
Target mixing Temperature	40/60: 170 to 190°C 70/100: 150 to 180°C 100/150: 140 to 170°C	

^{a)}Denotes Binder Penetration as specified

Recommendations of use

Surfacing Footpaths, Drives and Trench Reinstatements. Can be applied by Machine or Hand.

For further technical information regarding application, specification and use, consult the **Quarry Laboratory**.

^{b)} Supplied by the current approved sand source.

Issued by:

Ian Timberlake



Date Issued: 2/4/13