

QUALITY ASSURANCE SYSTEM – PRODUCT DATA SHEET

<u>Product reference N°</u>	AS18	Issue N° 7
<u>Product Description</u>	HRA 15/6F surf 40/60 or 100/150 ^{a)} PSV Proprietary Mix	
<u>Trade Description</u>	15% 6mm Basalt Sand Asphalt	
<u>Coarse Aggregate</u>	Basalt	
<u>Aggregate Fine</u>	Blend of Basalt Dust and Pit Sand ^{b)}	

Specification Details

John Wainwright Proprietary specification:

<u>Sieve Size</u>	<u>Conformance Specification</u>	<u>Declared Target</u>
10	98 – 100	100
6,3	89 – 100	97
4	82 – 96	89
2	71 – 81	76
0,500	47 – 55	51
0,250	24 – 32	28
0,063	10 – 14	12
Target Binder Content %	7,2 – 8,4	7,8
Minimum Layer Thickness	Machine 25mm	
Binder Penetration	Machine:	40/60 or 100/150
	Handlay:	Generally 100/150
Target mixing Temperature	100/150	140-170°C
Target Mixing Temperature	40/60	160-190°C

^{a)} Denotes Binder Penetration as specified

Recommendations of use

Surfacing Footpaths, Drives and Trench Reinstatements. Can be applied by Machine or Hand.

For further technical information regarding application, specification and use, consult the **Quarry Laboratory**.

^{b)} Supplied by the current approved sand source.

Issued by:

Ian Timberlake



Date Issued: 03/01/08