

QUALITY ASSURANCE SYSTEM – PRODUCT DATA SHEET

Product reference N° **CS9** **Issue N° 4**

Product Description **General Fill**

Trade Description **Quarry Waste**

Specification Details

Specification For Highway Works, Part 1, Table 6/2 (Acceptable Earthworks Material), Class 1C.

<u>BS Sieve Size</u>	<u>Grading Limits %</u>	<u>Typical Result %</u>
500mm	100	100
125mm	10 to 95	89
600mic	0 to 25	6
63mic	0 to 15	2

Comments

Uniformity Coefficient = **22**

Plasticity Index = **Non Plastic**

10% Fines Value (Soaked) = **80KN**

Recommendations of use

Generally suitable for the majority of imported granular fill applications. However, should not be sold without customers visual approval, especially where large Tonnage are involved.

For further Technical Information regarding application, specification and use, consult **Quarry Laboratory**.

Issued by:

Ian Timberlake



Date Issued: 07/09/06