QUALITY ASSURANCE SYSTEM – PRODUCT DATA SHEET

Product reference Nº **D10** **Issue Nº 2**

Product Description **AC 10 surf 160/220 fluxed PSV55**

Trade Description **10mm 28 day deferred**

Aggregate **All Basalt**

Specification Details

EN13108-1

Test Sieve (mm)	Conformance Specification	Declared Target
14	98 – 100	100
10	87 – 100	95
6,3	62 – 76	69
2	26 – 38	32
1	18 – 26	22
0,063	1 – 5	3
Declared Binder Content %	4.5 – 5.5	5.0

Nominal Layer Thickness (mm)	30 – 35	
Binder Penetration	Handlay:	160/220 fluxed
Target Mixing Temperature	70 to 90ºC	

Recommendations of use

For reinstatements, patch repairs, ramping off, potholes etc.

NOTE: As this material contains bitumen modified by the addition of light oil it may not obtain full strength immediately upon application.

For further technical information regarding application, specification and use, consult the **Quarry Laboratory.**

Issued by:
Ian Timberlake

Date Issued: 21/3/13

John Wainwright & Co Ltd Registered Office: Moons Hill Quarry Mendip Road Stoke St Michael Radstock BA3 5JU
Telephone: 01749 840274 Facsimile: 01749 841432 email: info@wainwright.co.uk Website: www.wainwright.co.uk

Sales - Telephone 01749 840111 **Surfacing** - Telephone 01749 841521 Facsimile: 01749 841520