

QUALITY ASSURANCE SYSTEM – PRODUCT DATA SHEET

Product reference N° MC7 **Issue N° 11**

Product Description AC 10 close surf 70/100, 100/150 or 160/220* PSV55

Trade Description As above, or 10mm Dense Surface Course

Aggregate All Basalt

Specification Details

EN13108-1

<u>Test Sieve (mm)</u>	<u>Conformance Specification</u>	<u>Declared Target</u>
14	98 – 100	100
10	87 – 100	95
6,3	59 – 73	66
2	25 – 37	31
1	18 – 26	22
0,063	4 – 8	6
Declared Binder Content %	5,0 – 6,0	5,5

Nominal Layer Thickness 30 – 40

Binder Penetration Machine: 70/100, 100/150 or 160/220 as specified
 Handlay: Generally 160/220

Target Mixing Temperature 160/200, 100/150 = 140 -170 °C - 70/100 = 150 -180 °C

* As specified

Recommendations of use


Accepted for material supplied under the Dorset, Somerset & Hampshire County Council Term Maintenance Contracts.

Surfacing Roads, Drives, Trench Reinstatements, Vehicle Parking Area's etc. requiring a minimum aggregate Polished Stone Value of **PSV55**

Can be applied by Machine or by Hand using skilled Labour.

For further technical information regarding application, specification and use, consult the **Quarry Laboratory**.

Issued by:
Ian Timberlake



Date Issued: 1/5/14