

QUALITY ASSURANCE SYSTEM – PRODUCT DATA SHEET

| | | |
|------------------------------------|---|-------------|
| <u>Product reference N°</u> | MC8 | Issue N° 11 |
| <u>Product Description</u> | AC 10 close surf 40/60, 70/100, 100/150 or 160/220* PSV60 | |
| <u>Trade Description</u> | As above, or 10mm Dense Surface Course | |
| <u>Aggregate</u> | 4/10 Coarse Gritstone Aggregate, remainder Basalt | |

Specification Details

EN13108-1

| <u>Test Sieve (mm)</u> | <u>Conformance Specification</u> | <u>Declared Target</u> |
|---------------------------|----------------------------------|------------------------|
| 14 | 98 – 100 | 100 |
| 10 | 87 – 100 | 95 |
| 6,3 | 59 – 73 | 66 |
| 2 | 25 – 37 | 31 |
| 1 | 18 – 26 | 22 |
| 0,063 | 4 – 8 | 6 |
| Declared Binder Content % | 5,0 – 6,0 | 5,5 |

Nominal Layer Thickness 30 – 40

Binder Penetration Machine: 40/60, 70/100, 100/150 or 160/220 as specified
Handlay: Generally 160/220

Target Mixing Temperature 160/200, 100/150 = 140 -170 °C - 70/100 = 150 -180 °C - 40/60: 160 to 190°C

* As specified

Recommendations of use

Accepted for material supplied under the Dorset, Somerset & Hampshire County Council Term Maintenance Contracts.

Formerly SWC9 of the South West Counties Regional Specification.


Surfacing Roads, Drives, Trench Reinstatements, Vehicle Parking Area's etc. Requiring a minimum aggregate Polished Stone Value of **PSV⁶⁰**

Can be applied by Machine or by Hand using skilled labour.

For other applications, contact the **Quarry Laboratory**.

Issued by:

Ian Timberlake



Date Issued: 21/3/13