

Polished Stone Value

Report No:	GLM0023454/488/S0	Report Date:	6 February 2015
Client:	JOHN WAINWRIGHT & CO LTD	Our Contract Ref:	50152592
Address:	STOKE QUARRY MENDIP RD STOKE ST MICHAEL RADSTOCK, AVON STOKE ST MICHAEL	Client Order No.:	P4Q098272
Client Contact:	Adriam Fisher	Sample No.:	5159488
Site:	Moons Hill Quarry	Client Sample Ref.:	720
Location:	No.2 Plant	Date Sampled:	01 Nov 14
Description:	10mm Basalt, Crushed Rock	Date Received:	14 Jan 15
Material Specification:	Not given	Date Tested:	04 Feb 15
Sample Type:	Bulk Bag	Material Supplier:	John Wainwright & Co Ltd
Depth:	Not given	Material Source:	Moons Hill Quarry
		Sampling Cert Received:	Yes
		Samples Submitted by:	Client
		Sampled by:	Client


Results :

		Mean of Specimen	Mean of Run	Mean of 4 Specimens	PSV
Test Run 1	Specimen 1	60.0	59.0	57.6	58
	Specimen 2	58.0			
Test Run 2	Specimen 3	56.0	56.2		
	Specimen 4	56.3			
Control Run 1	Specimen 1	51.0	50.0	49.1	
	Specimen 2	49.0			
Control Run 2	Specimen 3	48.0	48.2		
	Specimen 4	48.3			

Comments: 'New source used for control stone. A correction value of 49.0 was used in accordance with BSI update July 2011.

**Certified that the Polished Stone Value
 was determined in accordance with BS EN 1097-8: 2009**

Signed:



**Malcolm Lawson - Section Manager
 for and on behalf of Environmental Scientifics Group Limited**