

QUALITY ASSURANCE SYSTEM – PRODUCT DATA SHEET

<u>Product reference N°</u>	RB2	Issue N°5
<u>Product Description</u>	HRA 60/32 base 40/60 or 100/150^{a)} rec	
<u>Trade Description</u>	As above or 28mm Asphalt Roadbase	
<u>Aggregate</u>	Blend of Basalt Dust and Pit Sand ^{b)}	

Specification Details

EN13108-4

<u>Sieve Size (mm)</u>	<u>Conformance Specification</u>	<u>Declared Target</u>
40	98 - 100	100
31,5	90 - 100	99
20	61 - 79	70
14	46 - 64	55
2	30 – 44	37
0,500	21 – 31	26
0,250	11 – 21	16
0,063	1 – 7	4,0
Target Binder Content %	5,0 – 6,2	5,6
Nominal Layer Thickness (mm)	60 – 150	
Binder Penetration	Machine:	40/60 or 100/150 as specified
Target Mixing Temperature	40/60	160 to 190°C
	100/150	140 to 170°C

^{a)} Binder Penetration as specified

Recommendations of use

Normal Base applications.

For further technical information regarding application, specification and use, consult the **Quarry Laboratory**.

^{b)} Supplied by the current approved sand source.

Issued by:

Ian Timberlake



Date Issued: 3/4/13