

QUALITY ASSURANCE SYSTEM – PRODUCT DATA SHEET

Product reference N° **RB5** **Issue N° 2**

Product Description **0/32mm size single course, proprietary recipe mix**

Aggregate **All Basalt**

Specification Details


EN13108-1

<u>Sieve Size (mm)</u>	<u>Conformance Specification</u>	<u>Declared Target</u>
40	98 – 100	100
31.5	86 – 100	95
14	38 – 56	47
6,3	17 – 35	26
2	9 - 23	16
0.250	4 - 14	9
0,063	3 – 9	6
Target Binder Content %	3.5 – 4.7	4.1
Nominal Layer Thickness (mm)	70 – 150	
Binder Penetration	Machine: 100/150 Handlay: 100/150	
Target Mixing Temperature	100/150	140 to 170°C

Recommendations of use

Can be used either as a combined surface and binder course if blinded immediately after laying or it may be used as a binder course.

For further technical information regarding application, specification and use, consult the Quarry Laboratory.

Issued by:
Ian Timberlake 

Date Issued: 3/4/13